EXHIBIT E

Expert Report of William E. Longo, Ph.D., Prepared on Behalf of the Property Damage Asbestos Claimants Represented by the Law Firm of Dies & Hile, LLP

Appendix E

State of Texas – Building Inspections

October 25, 2006

M40633 & M40632

MAS

M40633 & M40632

STATE OF TEXAS

Table of Contents

SECTION 1

State of Texas
WR Grace Asbestos Inspections

1001 Louisiana Street - Houston, Texas (aka: El Paso Bldg)
Field Notes 9/19/06 – 9/20/06

Bldg. 32-story
Fireproofing on each floor applied to structural steel members, I beams and corrugated metal pan decking

Fireproofing overspray present on perimeter and core walls at the roof deck interface. Evidence of obvious fireproofing delamination observed in each of the penetrations made to the suspended ceiling during the plenum inspection.

The fireproofing present is a vermiculite based material with a taupe colored appearance (identified as a WR Grace product). Inspection of horizontal surfaces below the decking (in the plenum space), revealed that most surfaces are covered with a fine layer of dust and debris from disturbance and/or delamination of the fireproofing. In many areas, pea sizes to fist size chunks of fireproofing debris are also present.

The ceilings in the leasable/occupied areas of building are generally constructed of 5'x5' metal grid panels each containing 4 fiberglass ceiling tiles and a fluorescent light fixture. Access to the plenum is accomplished by removing the plastic light diffuser lense from the light and the rotating two levers in the lighting fixture which allow the light box to swing open in the frame (opposite its hinged side) towards the floor. This swinging action allows the fireproofing dust and debris (which have accumulated on top of the light) to fall into the occupied space below.

The acoustical plaster present was as a WR Grace product. The acoustical plaster present appears to be a spray applied material generally utilized on the ceilings in the central core area of the building and in the subterranean hallways connecting the subject building to other buildings.

According to the building engineers, renovation work has taken place thru-out the building (primarily consisting of modifications below the ceiling) but there have been spot abatements of the fireproofing (FP) as necessary. No widespread or full floor abatements have been conducted.

LOCATION OF CEILING PENETRATIONS AND INSPECTIONS AREAS

24th floor – adjacent to Data Room W2412B
Photos 209-211

LOCATION OF CEILING PENETRATIONS AND INSPECTIONS AREAS (cont)

21st floor – adjacent to Office N2132A
Photos 212-218

17th floor – adjacent to Office S1704A
Photos 219-221

17th floor – elevator lounge area
Photos 222-225

12th floor – adjacent to Office E1244A
Photos 226-231

6th floor – adjacent to Office S601
Photos 232-237

25th floor – north side of elevator lobby
Photos 238-239

B floor – in tunnel at El Paso display case
Photos 240-241

10th floor – in W10111B small conference Rm.
Photos 57-58

6th floor – in S603B ethics file room
Photos 59-60

1st floor – in the pipe shaft outside stairwell D
Photos 61-63

State of Texas
WR Grace Asbestos Inspections

611 Walker Street - Houston, Texas (aka: Public Works Building and Annex)
Field Notes 9/20/06

Bldg. 27-story plus 6-story annex
The original fireproofing was applied to structural steel members, I beams and corrugated metal pan decking in the main tower and in the adjoining annex. The fireproofing has since been abated from most of the tower building but is known to remain in the bathrooms on each floor (above hard plaster ceilings), on the exterior columns surrounding the building (encased in concrete) and certain pipe chases of that building. Abatement of the fireproofing has reportedly been completed in most areas of the annex as well with the exception of fireproofing in the bridge connecting the two buildings (located above a light weight concrete deck) and a few other sporadic inaccessible areas.

The fireproofing present is a vermiculite based material with a taupe colored appearance (identified as a WR Grace product). Inspection of horizontal surfaces below the decking (in the plenum space), revealed that most surfaces are covered with a fine layer of dust and debris from disturbance and/or delamination of the fireproofing. In many areas, pea sizes to fist size chunks of fireproofing debris are also present.

Note: a limited number of dust samples were collected from this building due to the location of the remaining original fireproofing located in limited access area

LOCATION OF CEILING PENETRATIONS AND INSPECTIONS AREAS

20th floor – in NE Fresh Air Shaft
Photos 64-66

10th floor – in Room 1003
Photo 67

5th floor – in NE Fresh Air Shaft
Photos 68-69

Annex 6th Floor – inside wall chase adjacent to Women's restroom
Photos 70-72

State of Texas
WR Grace Asbestos Inspections

Amarillo Air Terminal - Amarillo, Texas
Field Notes 9/21/06

Terminal Bldg. 3-story
Originally fireproofing was applied to structural steel members, I beams and metal pan decking generally throughout the building. Over the course of many years the fireproofing has been abated from most of the building, but is known to remain in at least 3 major areas:

- a second floor airport storage area in Terminal 30
- the basement mechanical room and adjacent areas in the main terminal, and
- the third floor office area and mechanical rooms in the main terminal

In the mechanical rooms the fireproofing is directly accessible to occupants since no suspended or rigid ceiling is present.

The fireproofing present is a vermiculite based material with a taupe colored appearance (identified as a WR Grace product). Inspection of horizontal surfaces below the decking (in the plenum space), revealed that most surfaces are covered with a fine layer of dust and debris from disturbance and/or delamination of the fireproofing. In many areas, pea sizes to fist size chunks of fireproofing debris are also present.

LOCATION OF CEILING PENETRATIONS AND INSPECTIONS AREAS

Concourse 30 - Second Level airport Storage (behind Air Host)
Photos 73-78

Main Terminal - Basement Level Mechanical Room – storage room area
Photos 79-88

Main Terminal - Basement Level Mechanical Room – hallway outside Women's Rest room
Photos 89-91

Main Terminal - 3rd Floor Air Handler Room
Photos 92-94

Main Terminal - 3rd Floor Men's Rest Room
Photos 95-100

State of Texas
WR Grace Asbestos Inspections

1000 South Polk Street - Amarillo, Texas (aka: Bivins Building -Chamber of Commerce)
Field Notes 9/21/06

Located in downtown Amarillo, originally this building was constructed as a residential home (3-story plus basement)

An acoustical treatment has been applied to certain section of the plaster ceilings on the basement, first and second floors (on or about 1971).

The plaster present is vermiculite based textured finish with a taupe colored appearance. Inspection of many of the horizontal surfaces observed below the ceiling are covered with a fine layer of dust and fine debris from delamination and/or disturbance of the acoustical plaster.

LOCATION OF CEILING PENETRATIONS AND INSPECTIONS AREAS

Basement Floor in back hallway at janitors storage area
Photos 101-104

1st Floor City Counsel Chambers (above suspended ceiling)
Photos 105-110

2nd Floor Hallway and copy area outside Conference Room
Photos 111-114

SECTION 2

MAS

Materials Analytical Services

Micro-Vac Dust Sampling
Chain-of-Custody

Project No.: 16090601 Date: 9/25/06

Location: Various Texas Bldgs City/State: Houston and Ammarillo

Sample #	Sample Date	General Sample Location	Sample Surface	Sample Area*	Comments
1	9/19/2006	El Paso 24th Floor, adjacent to W2412B	Top of HVAC Duct	100	Fp
2	9/19/2006	El Paso 21st Floor, adjacent to N2132A	Top of FLF supply duct	100	Fp
3	9/19/2006	El Paso 17th Floor, adjacent to S1704A	Top of HVAC Duct	100	Fp
4	9/19/2006	El Paso 17th Floor, elevator lounge area	Top of partion wall nxt to sofa	100	Ap
5	9/19/2006	El Paso 12th Floor, adjacent to E1244A	Top of FLF supply duct	100	Fp
6	9/19/2006	El Paso 6th Floor, adjacent to S601	Top of HVAC Duct	100	Fp
7	9/19/2006	El Paso 25th Floor, elevator lobby - northside	Top of wall sconce	100	Ap
8	9/19/2006	El Paso B Floor, tunnel at El Paso display case	Top of display case	100	Fp
9	9/20/2006	El Paso 10th Floor, in W1011B	Top of foil wrapped HVAC duct	37 mm	Fp - contact sample
10	9/20/2006	El Paso 6th Floor, in S603B	Top of FLF supply duct	37 mm	Fp - contact sample
11	9/20/2006	El Paso 1st Floor, in pipeshaft adj to stairwell D	Top of metal HVAC duct	37 mm	Fp - contact sample
1	9/20/2006	PWB 20th Floor Fresh Air Shaft NE Corner	Top of metal pipe	100	Fp
2	9/20/2006	PWB 6th Floor Annex Inside wall Chase	Top of metal pipe	100	Fp
1	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	100	Fp
2	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	37 mm	Fp - contact sample
3	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	100	Fp
4	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	37 mm	Fp - contact sample
5	9/21/2006	AAT B floor, Hallway outside Womens's RR	Top of FLF	100	Fp
6	9/21/2006	AAT 3rd floor, Mens Restroom	Top of HVAC duct	100	Fp
1	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	100	Ap
2	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	37mm	Ap - contact sample
3	9/21/2006	Bivins 1st Floor, City Counsel Chambers	Top of 2X4 lay-in ceiling tile	100	Ap
4	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	100	Ap
5	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	37mm	Ap - contact sample

Sampled by:Martin Bennett

Turnaround Time: __X__ standard or ____ rush

*preferred sample collection area should be 100cm² or greater

Received: _____ Date: _____

Dust Samples

MAS

m40633

Materials Analytical Services

Micro-Vac Dust Sampling
Chain-of-Custody

Project No.: 16090601 Date: 9/25/06

Location: Various Texas Bldgs City/State: Houston and Ammarillo

Sample #	Sample Date	General Sample Location	Sample Surface	Sample Area*	Comments
1	9/19/2006	El Paso 24th Floor, adjacent to W2412B	Top of HVAC Duct	100	Fp
2	9/19/2006	El Paso 21st Floor, adjacent to N2132A	Top of FLF supply duct	100	Fp
3	9/19/2006	El Paso 17th Floor, adjacent to S1704A	Top of HVAC Duct	100	Fp
4	9/19/2006	El Paso 17th Floor, elevator lounge area	Top of partion wall nxt to sofa	100	Ap
5	9/19/2006	El Paso 12th Floor, adjacent to E1244A	Top of FLF supply duct	100	Fp
6	9/19/2006	El Paso 6th Floor, adjacent to S601	Top of HVAC Duct	100	Fp
7	9/19/2006	El Paso 25th Floor, elevator lobby - northside	Top of wall sconce	100	Ap
8	9/19/2006	El Paso B Floor, tunnel at El Paso display case	Top of display case	100	Fp
9	9/20/2006	El Paso 10th Floor, in W1011B	Top of foil wrapped HVAC duct	37 mm	Fp - contact sample
10	9/20/2006	El Paso 6th Floor, in S603B	Top of FLF supply duct	37 mm	Fp - contact sample
11	9/20/2006	El Paso 1st Floor, in pipeshaft adj to stairwell D	Top of metal HVAC duct	37 mm	Fp - contact sample
1	9/20/2006	PWB 20th Floor Fresh Air Shaft NE Corner	Top of metal pipe	100	Fp
2	9/20/2006	PWB 6th Floor Annex Inside wall Chase	Top of metal pipe	100	Fp
1	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	100	Fp
2	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	37 mm	Fp - contact sample
3	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	100	Fp
4	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	37 mm	Fp - contact sample
5	9/21/2006	AAT B floor, Hallway outside Womens's RR	Top of FLF	100	Fp
6	9/21/2006	AAT 3rd floor, Mens Restroom	Top of HVAC duct	100	Fp
1	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	100	Ap
2	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	37mm	Ap - contact sample
3	9/21/2006	Bivins 1st Floor, City Counsel Chambers	Top of 2X4 lay-in ceiling tile	100	Ap
4	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	100	Ap
5	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	37mm	Ap - contact sample

Sampled by:Martin Bennett

*preferred sample collection area should be 100cm² or greater

Hand Delivered

Turnaround Time: __X__ standard or ____ rush

Received: Nancy Sears Date: 9/28/06

MATERIALS ANALYTICAL SERVICES
PROJECT COC

MAS ID:	M40633	**Client Job No:**	16090601
Client Name:	Dies and Hile, LLP	**Client PO:**	
Project Name:	Houston and Amarillo	**Date In:**	9/25/2006
Logged By:	dmazzaferro	**Client Code:**	0380

TRANSPORT INFORMATION:

Submitted By:	Martin Bennett	**Documents:**	COC
Delivery By:	Hand Delivery		
Received By:	Nancy Sears	**Comments for COC:**	
Condition:	goodc		

CONTACT INFORMATION:

Contact:	Martin Dies			**Work Phone:** (409) 883-4394	**Ext:**
Title:	**First Name**	**Last Name:**	**Suffix**	**Other Phone**	**Ext:**
Mr.	Martin	Dies		**Fax:** (409) 883-4814	

SAMPLE INFORMATION:

#	Client ID	Volume	#	Client ID	Volume
000	lab blank	0	016	Bivins 3	100
001	El Paso 1	100	017	Bivins 4	100
002	El Paso 2	100			
003	El Paso 3	100			
004	El Paso 4	100			
005	El Paso 5	100			
006	El Paso 6	100			
007	EL Paso 7	100			
008	El Paso 8	100			
009	PWB 1	100			
010	PWB 2	100			
011	AAT 1	100			
012	AAT 3	100			
013	AAT 5	100			
014	AAT 6	100			
015	Bivins 1	100			

SIGNATURES

RECEIVED BY: _____ **ANALYZED BY:** _____

REVIEWED BY: _____ **REPORTED BY:** _____

PREPARED BY: _____ **DEPOSED BY:** _____

Contact Samples

M40632

MAS

Materials Analytical Services

Micro-Vac Dust Sampling
Chain-of-Custody

Project No.: 16090601 Date: 9/25/06

Location: Various Texas Bldgs City/State: Houston and Ammarillo

Sample #	Sample Date	General Sample Location	Sample Surface	Sample Area	Comments
1	9/19/2006	El Paso 24th Floor, adjacent to W2412B	Top of HVAC Duct	100	Fp
2	9/19/2006	El Paso 21st Floor, adjacent to N2132A	Top of FLF supply duct	100	Fp
3	9/19/2006	El Paso 17th Floor, adjacent to S1704A	Top of HVAC Duct	100	Fp
4	9/19/2006	El Paso 17th Floor, elevator lounge area	Top of partion wall nxt to sofa	100	Ap
5	9/19/2006	El Paso 12th Floor, adjacent to E1244A	Top of FLF supply duct	100	Fp
6	9/19/2006	El Paso 6th Floor, adjacent to S601	Top of HVAC Duct	100	Fp
7	9/19/2006	El Paso 25th Floor, elevator lobby - northside	Top of wall sconce	100	Ap
8	9/19/2006	El Paso B Floor, tunnel at El Paso display case	Top of display case	100	Fp
9	9/20/2006	El Paso 10th Floor, in W1011B	Top of foil wrapped HVAC duct	37 mm	Fp - contact sample
10	9/20/2006	El Paso 6th Floor, in S603B	Top of FLF supply duct	37 mm	Fp - contact sample
11	9/20/2006	El Paso 1st Floor, in pipeshaft adj to stairwell D	Top of metal HVAC duct	37 mm	Fp - contact sample
1	9/20/2006	PWB 20th Floor Fresh Air Shaft NE Corner	Top of metal pipe	100	Fp
2	9/20/2006	PWB 6th Floor Annex Inside wall Chase	Top of metal pipe	100	Fp
1	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	100	Fp
2	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	37 mm	Fp - contact sample
3	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	100	Fp
4	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	37 mm	Fp - contact sample
5	9/21/2006	AAT B floor, Hallway outside Womens's RR	Top of FLF	100	Fp
6	9/21/2006	AAT 3rd floor, Mens Restroom	Top of HVAC duct	100	Fp
1	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	100	Ap
2	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	37mm	Ap - contact sample
3	9/21/2006	Bivins 1st Floor, City Counsel Chambers	Top of 2X4 lay-in ceiling tile	100	Ap
4	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	100	Ap
5	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	37mm	Ap - contact sample

Sampled by:Martin Bennett

Turnaround Time: __X__ standard or ____ rush

*preferred sample collection area should be 100cm² or greater

Received: Amarillo Date: 9/25/06

MATERIALS ANALYTICAL SERVICES
PROJECT COC

MAS ID:	m40632	**Client Job No:**	16090601
Client Name:	Law Offices of Martin Dies	**Client PO:**	
Project Name:	Houston and Amarillo	**Date In:**	9/25/2006
Logged By:	dmazzaferro	**Client Code:**	0380

TRANSPORT INFORMATION:

Submitted By:	Martin Bennett	**Documents:**	COC
Delivery By:	Hand Delivery		
Received By:	Nancy Sears	**Comments for COC:**	
Condition:	good		

CONTACT INFORMATION:

Contact:	Martin Dies			**Work Phone:** (409) 883-4394	**Ext:**
Title:	**First Name**	**Last Name:**	**Suffix**	**Other Phone**	**Ext:**
Mr.	Martin	Dies		**Fax:** (409) 883-4814	

SAMPLE INFORMATION:

#	Client ID	Volume	#	Client ID	Volume
001	9 EIP				
002	10 EIP				
003	11EIP				
004	2 AAT				
005	4 AAT				
006	2 Biv				
007	5 Biv				

SIGNATURES

RECEIVED BY: _____ **ANALYZED BY:** _____

REVIEWED BY: _____ **REPORTED BY:** _____

PREPARED BY: _____ **DEPOSED BY:** _____

SECTION 3

MAS

Materials Analytical Services

Micro-Vac Dust Sampling
Summary of Results

Project No.: 16090601 Date: 9/25/06

Location: Various Texas Bldgs City/State: Houston and Ammarillo

Sample #	Sample Date	General Sample Location	Sample Surface	Asbestos Structures Counted	Asbestos (Conc.) Str/Ft^2	Asbestos (Conc.) Str/Cm^2	Relative Contamination Level*
1	9/19/2006	El Paso 24th Floor, adjacent to W2412B	Top of HVAC Duct	101	$8.99x10^9$	$9.67x10^6$	FP - Extreme
2	9/19/2006	El Paso 21st Floor, adjacent to N2132A	Top of FLF supply duct	108	$8.54x10^9$	$9.19x10^6$	FP - Extreme
3	9/19/2006	El Paso 17th Floor, adjacent to S1704A	Top of HVAC Duct	45	$2.94x10^9$	$3.17x10^6$	FP - Extreme
4	9/19/2006	El Paso 17th Floor, elevator lounge area	Top of partion wall nxt to sofa	13	$1.85x10^7$	$1.99x10^4$	AP - Moderate
5	9/19/2006	El Paso 12th Floor, adjacent to E1244A	Top of FLF supply duct	66	$9.00x10^9$	$9.69x10^6$	FP - Extreme
6	9/19/2006	El Paso 6th Floor, adjacent to S601	Top of HVAC Duct	100	$2.18x10^{10}$	$2.35x10^7$	FP - Extreme
7	9/19/2006	El Paso 25th Floor, elevator lobby - northside	Top of wall sconce	16	$8.87x10^7$	$9.55x10^4$	AP - Moderate
8	9/19/2006	El Paso B Floor, tunnel at El Paso display case	Top of display case	137	$5.60x10^{10}$	$6.03x10^7$	FP - Extreme
9	9/20/2006	El Paso 10th Floor, in W1011B	Top of foil wrapped HVAC duct				
10	9/20/2006	El Paso 6th Floor, in S603B	Top of FLF supply duct				
11	9/20/2006	El Paso 1st Floor, in pipeshaft adj to stairwell D	Top of metal HVAC duct				
1	9/20/2006	PWB 20th Floor Fresh Air Shaft NE Corner	Top of metal pipe	10	$5.52x10^7$	$5.94x10^4$	FP - Moderate
2	9/20/2006	PWB 6th Floor Annex Inside wall Chase	Top of metal pipe	76	$1.15x10^{10}$	$1.23x10^7$	FP - Extreme
1	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF	116	$1.28x10^{10}$	$1.38x10^7$	FP - Extreme
2	9/21/2006	AAT Concourse 30 2nd floor, Airport Storage	Top of FLF				
3	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf	98	$1.16x10^{11}$	$1.25x10^8$	FP - Extreme
4	9/21/2006	AAT B floor, Mechanical.Rm (supply area)	Top of Storage Shelf				
5	9/21/2006	AAT B floor, Hallway outside Womens's RR	Top of FLF	101	$1.12x10^{10}$	$1.20x10^7$	FP - Extreme
6	9/21/2006	AAT 3rd floor, Mens Restroom	Top of HVAC duct	64	$7.38x10^9$	$7.94x10^6$	FP - Extreme
1	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct	51	$2.81x10^9$	$3.03x10^6$	AP - Extreme
2	9/21/2006	Bivins B floor, in janitors storage area off hallway	Top of metal HVAC duct				
3	9/21/2006	Bivins 1st Floor, City Counsel Chambers	Top of 2X4 lay-in ceiling tile	30	$3.51x10^9$	$3.78x10^6$	AP - Extreme
4	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF	73	$9.96x10^{10}$	$1.07x10^8$	AP - Extreme
5	9/21/2006	Bivins 2nd floor, copy area outside conference rm	Top of FLF				

SECTION 4

Dust Samples

TEM DUST ANALYSIS M40633 000

Dies and Hile, LLP
Houston and Amarillo

Client Sample ID: 0

Sample Area/ Volume:	0 Liter	Date Analyzed:	10/11/2006
Filter Type:	MCE 47mm	Analyst:	Kevin Simpson
Pore size:	0.45	Scope Number:	3
Effective Filter Area:	1297	Accelerating Voltage:	100 KV
Sample type:	Dust	Indicated Mag:	25 KX
Analysis type:	Dust	Screen Mag:	20 KX
Grid Acceptance	Yes 1 %	Grid_box:	7186

Str < 5um:	0	Number of grids:	2	#1: 105	#3: 106	Average Grid Size:	0.010920
Str ≥5um:	0	Number of openings:	10	#2: 103	#4: 104	Total Area Analyzed:	0.109
Total Str:	0						

Volume Filtered 50 ml
Dilution Factor 0

Str / sqr ft	0.000E+00	Str / cm2	0.000E+00
Str / sqr ft >=5	0.000E+00	Str / cm2 >=5	0.000E+00

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
	A6-F10		NSD					☐	☐	☐
	F9		NSD					☐	☐	☐
	F8		NSD					☐	☐	☐
	F7		NSD					☐	☐	☐
	F6		NSD					☐	☐	☐
	E5-C9		NSD					☐	☐	☐
	C8		NSD					☐	☐	☐
	C7		NSD					☐	☐	☐
	C6		NSD					☐	☐	☐
	C5		NSD					☐	☐	☐

M40633 000

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

El Paso Building

1001 Louisiana Street

TEM DUST ANALYSIS M40633 001

Dies and Hile, LLP
Houston and Amarillo

Client Sample ID: El Paso 1

Sample Area/ Volume:	100 cm2	Date Analyzed:	10/17/2006
Filter Type:	MCE 47mm	Analyst:	MDMOUNT
Pore size:	0.45	Scope Number:	2
Effective Filter Area:	1297	Accelerating Voltage:	100 KV
Sample type:	Dust	Indicated Mag:	25 KX
Analysis type:	Dust	Screen Mag:	20 KX
Grid Acceptance	YES 5 %	Grid_box:	7195

Str <5um:	79	Number of grids:	2	#1: 92	#3: 92	Average Grid Size:	0.008464
Str ≥5um:	22	Number of openings:	8	#2: 92	#4: 92	Total Area Analyzed:	0.068
Total Str:	101						
Volume Filtered	0.2 ml	Str / sqr ft	8.987E+09			Str / cm2	9.673E+06
Dilution Factor	500	Str / sqr ft >=5	1.957E+09			Str / cm2 >=5	2.107E+06

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
1	E10-D5	C	C-B	20.00	0.20	X	M25803	✔	✔	
2		C	M-F	4.00	0.05	X	X	✔		
3		C	B	1.40	0.03	X	X	✔		
4		C	B	1.20	0.10	X	X	✔		
5		C	M-F	2.30	0.03	X	X	✔		
6		C	C-F	10.50	0.03	X	X	✔		
7		C	B	4.10	0.05	X	X	✔		
8		C	C-F	5.50	0.05	X				
9		C	C-B	6.00	0.03	X	X	✔		
10		C	M-F	1.60	0.05	X	X	✔		
11		C	M-F	15.00	0.05	X				
12		C	M-B	2.00	0.40	X				
13	F3	C	B	4.00	0.38	X				

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
14		C	M-F	6.00	0.03	X		☐	☐	☐
15		C	F	6.40	0.05	X		☐	☐	☐
16		C	M-F	0.80	0.02	X		☐	☐	☐
17		C	C-F	10.00	0.05	X		☐	☐	☐
18		C	F	0.80	0.03	X		☐	☐	☐
19		C	B	3.00	0.10	X		☐	☐	☐
20		C	C-B	3.00	0.20	X	X	☑	☐	☐
21		C	M-F	2.80	0.03	X		☐	☐	☐
22		C	F	2.00	0.03	X		☐	☐	☐
23	H2	C	M-F	1.60	0.05	X		☐	☐	☐
24		C	M-B	1.50	0.20	X		☐	☐	☐
25		C	M-F	1.20	0.03	X		☐	☐	☐
26		C	M-B	3.00	0.20	X		☐	☐	☐
27		C	C-F	1.40	0.03	X		☐	☐	☐
28		C	B	5.00	0.20	X		☐	☐	☐
29		C	M-B	2.30	0.03	X		☐	☐	☐
30		C	M-F	2.60	0.05	X	X	☑	☐	☐
31		C	B	2.20	0.10	X		☐	☐	☐
32		C	M-F	6.00	0.03	X		☐	☐	☐
33	H5	C	M-F	12.00	0.03	X		☐	☐	☐
34		C	F	16.00	0.03	X		☐	☐	☐
35		C	C-F	3.00	0.03	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
36		C	F	5.00	0.03	X		☐	☐	☐
37		C	F	9.00	0.03	X		☐	☐	☐
38		C	M-F	3.00	0.03	X		☐	☐	☐
39		C	C-F	2.00	0.03	X		☐	☐	☐
40		C	C-B	4.00	0.10	X	X	☑	☐	☐
41	I9	C	C-B	1.20	0.10	X		☐	☐	☐
42		C	C-B	16.00	0.20	X		☐	☐	☐
43		C	C-B	1.00	0.10	X		☐	☐	☐
44		C	B	2.60	0.20	X		☐	☐	☐
45		C	C-F	3.60	0.03	X		☐	☐	☐
46		C	C-B	1.20	0.10	X		☐	☐	☐
47		C	B	3.20	0.20	X		☐	☐	☐
48		C	C-F	1.20	0.05	X		☐	☐	☐
49		C	C-F	1.40	0.20	X		☐	☐	☐
50		C	F	1.20	0.03	X	X	☑	☐	☐
51		AM	B	40.00	6.00	X	X	☑	☑	☐
52	E9-E3	C	C-B	2.00	0.20	X		☐	☐	☐
53		C	C-B	1.70	0.10	X		☐	☐	☐
54		C	F	2.20	0.05	X		☐	☐	☐
55		C	F	3.20	0.05	X		☐	☐	☐
56		C		1.50	0.05	X		☐	☐	☐
57		C	B	6.00	0.08	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
58		C	M-F	1.20	0.03	X		☐	☐	☐
59		C	M-B	2.20	0.05	X		☐	☐	☐
60		C	F	0.80	0.02	X	X	☑	☐	☐
61		C	M-F	1.20	0.03	X		☐	☐	☐
62		C	B	1.20	0.03	X		☐	☐	☐
63		C	F	0.80	0.02	X		☐	☐	☐
64		C	M-F	2.20	0.03	X		☐	☐	☐
65	H3	C	F	1.00	0.02	X		☐	☐	☐
66		C	F	1.20	0.02	X		☐	☐	☐
67		C	M-F	0.80	0.02	X		☐	☐	☐
68		C	M-F	3.00	0.05	X		☐	☐	☐
69		C	B	2.40	0.20	X		☐	☐	☐
70		C	M-F	12.00	0.05	X	X	☑	☐	☐
71		C	C-F	1.20	0.03	X		☐	☐	☐
72		C	C-F	1.40	0.01	X		☐	☐	☐
73		C	F	11.00	0.05	X		☐	☐	☐
74		C	C-F	1.70	0.03	X		☐	☐	☐
75		C	F	1.80	0.05	X		☐	☐	☐
76		C	F	0.80	0.02	X		☐	☐	☐
77		C	F	2.20	0.03	X		☐	☐	☐
78		C	B	3.80	0.10	X		☐	☐	☐
79		C	C-B	3.00	0.03	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
80		C	M-F	1.40	0.05	X	X	☑	☐	☐
81		C	C-F	0.80	0.03	X		☐	☐	☐
82		C	C-F	0.80	0.02	X		☐	☐	☐
83	I5	C	F	0.80	0.02	X		☐	☐	☐
84		C	M-F	2.00	0.03	X		☐	☐	☐
85		C	C-F	1.00	0.03	X		☐	☐	☐
86		C	B	1.60	0.20	X		☐	☐	☐
87		C	F	5.20	0.10	X		☐	☐	☐
88		C	M-F	1.00	0.03	X		☐	☐	☐
89		C	M-F	0.80	0.03	X		☐	☐	☐
90		C	M-F	7.00	0.05	X		☐	☐	☐
91		C	C-B	1.40	0.10	X	X	☑	☐	☐
92		C	M-B	3.80	0.05	X		☐	☐	☐
93		C	M-F	1.20	0.03	X		☐	☐	☐
94		C	M-F	13.00	0.05	X		☐	☐	☐
95		C	M-F	1.00	0.05	X		☐	☐	☐
96		C	M-F	3.60	0.02	X		☐	☐	☐
97		C	F	2.30	0.03	X		☐	☐	☐
98		C	F	1.20	0.03	X		☐	☐	☐
99		C	F	1.00	0.02	X		☐	☐	☐
100		C	C-F	2.30	0.05	X		☐	☐	☐
101		C	C-F	1.50	0.05	X	X	☑	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
									M40633	001

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster


Realtime: 38.7
Livetime: 36.2
M40633-001 Chrysotile Scr # 1
103
77
51
25
Counts
Mg
Si
Cu
Fe
Cu
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 28.3
Livetime: 22.0
M40633-001 Chrysotile Str # 2::
Counts
103
77
51
25
Mg
Si
Cu
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 24.1
M40633-001 Chrysotile Ste # 3::
Counts
184
138
92
46
Cu
Cu
Mg
Si
Fe
Cu
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.6
Livetime: 28.9
M40633-001 Chrysotile Str # 4::
138
103
69
34
Counts
Mg
Si
Cu
Cu
Cu
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 23.9
M40633-001 Chrysotile Str # 5:1
Counts
138
103
69
34
Si
Mg
Cu
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 25.1
M40633-001 Chrysotile Str.# 6::
138
103
69
34
Counts
Si
Cu
Mg
Cl
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (keV)


Realtime: 30.3
Livetime: 26.5
M40683-001 Chrysotile Str # 7:
328
246
164
82
Counts
Mg
Si
O
Cu
Cu
Fe
Cu
Cl
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 35.6
Livetime: 33.1
M4D633-001 Chrysotile Str # 9::
184
138
92
46
Counts
Mg
Si
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 32.8
Livetime: 31.1
M40633-001 Chrysotile Str # 10:1
103
77
51
25
Counts
Mg
Si
Fe
Cu
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.6
Livetime: 28.9
M40633-001 Chrysotile Str # 20::
103
77
51
25
Counts
Mg
Si
Cu
Fe
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 32.1
Livetime: 25.3
M40633-001 Chrysotile Str # 30::
C
Si
Mg
Cu
Cu
Cu
Fe
Cu
Counts
103
77
51
25
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.5
Livetime: 28.9
M40633-001 Chrysotile Str # 40::
103
77
51
25
Counts
Mg
Si
Cu
Cu
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 20.5
M40633-001 Chrysotile Str # 50::
Counts
246
184
123
61
Si
Mg
Cu
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (keV)


Realtime: 31:1
Livetime: 28.3
M40633-001 Chrysotile Sc
205
153
102
51
Counts
Si
Cu
Mg
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 23.8
M40633-001 Chrysotile Str # 60::
C
Cu
Cu
Mg
Si
Cl
Fe
Counts
138
103
69
34
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 23.3
M40638-001 Chrysotile Str # 70::
C
Mg
Si
Cu
Cu
Fe
Cu
138
103
69
34
Counts
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.8
Livetime: 24.5
M40633-001 Chrysotile Std # 801
C
Cu
Mg
Si
Cu
Fe
Cu
138
103
69
34
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (keV)


Realtime: 58.8
Livetime: 55.6
M40633-001 Chrysotile Str.#-91:
103
77
51
25
Counts
Cu
Si
Mg
Fe
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 34.7
Livetime: 31.4
M40683-001 Chrysotile Str # 101:
Counts
103
77
51
25
Si
Mg
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)

TEM DUST ANALYSIS M40633 002

Dies and Hile, LLP
Houston and Amarillo

Client Sample ID: El Paso 2

Sample Area/ Volume:	100 cm2	Date Analyzed:	10/18/2006
Filter Type:	MCE 47mm	Analyst:	MDMOUNT
Pore size:	0.45	Scope Number:	2
Effective Filter Area:	1297	Accelerating Voltage:	100 KV
Sample type:	Dust	Indicated Mag:	25 KX
Analysis type:	Dust	Screen Mag:	20 KX
Grid Acceptance	YES 5 %	Grid_box:	7195

Str < 5um:	59	Number of grids:	2	#1: 92	#3: 92	Average Grid Size:	0.008464
Str ≥5um:	49	Number of openings:	9	#2: 92	#4: 92	Total Area Analyzed:	0.076
Total Str:	108						

Volume Filtered	0.2 ml	Str / sqr ft	8.542E+09
Dilution Factor	500	Str / sqr ft >=5	3.875E+09
		Str / cm2	9.194E+06
		Str / cm2 >=5	4.171E+06

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
1	D10-D4	C	M-F	3.00	0.03	X	M25807	☑	☐	☐
2		C	C-F	8.00	0.05	X	X	☑	☐	☐
3		C	C-B	15.00	0.05	X	X	☑	☐	☐
4		C	M-F	4.00	0.03	X	X	☑	☐	☐
5		C	C-F	3.00	0.10	X	X	☑	☐	☐
6		C	M-F	6.00	0.03	X	X	☑	☐	☐
7		C	M-F	1.80	0.03	X	X	☑	☐	☐
8		C	C-B	7.00	0.10	X	X	☑	☐	☐
9		C	C-B	3.40	0.10	X	X	☑	☐	☐
10		C	M-F	20.00	0.05	X		☐	☐	☐
11		C	M-B	11.00	0.10	X		☐	☐	☐
12		C	F	3.60	0.03	X		☐	☐	☐
13	D7	C	B	2.20	0.20	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
14		C	F	8.00	0.05	X		☐	☐	☐
15		C	F	2.20	0.03	X		☐	☐	☐
16		C	M-B	2.00	0.20	X		☐	☐	☐
17		C	M-F	15.00	0.08	X		☐	☐	☐
18		C	B	3.50	0.12	X		☐	☐	☐
19		C	M-F	1.20	0.03	X		☐	☐	☐
20	G7	C	F	2.00	0.03	X	X	☑	☐	☐
21		C	B	22.00	0.05	X		☐	☐	☐
22		C	B	1.30	0.05	X		☐	☐	☐
23		C	M-F	2.50	0.05	X		☐	☐	☐
24		C	B	10.00	0.20	X		☐	☐	☐
25		C	F	12.00	0.05	X		☐	☐	☐
26		C	B	7.80	0.15	X		☐	☐	☐
27		C	F	4.20	0.02	X		☐	☐	☐
28	H3	C	F	0.80	0.02	X		☐	☐	☐
29		C	F	14.00	0.12	X		☐	☐	☐
30		C	C-B	32.00	0.10	X	X	☑	☐	☐
31		C	C-F	14.00	0.05	X		☐	☐	☐
32		C	F	5.20	0.05	X		☐	☐	☐
33		C	M-B	12.00	0.20	X		☐	☐	☐
34		C	C-B	1.00	0.05	X		☐	☐	☐
35		C	B	4.00	0.20	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
36		C	C-B	3.00	0.20	X		☐	☐	☐
37	F3	C	F	1.20	0.02	X		☐	☐	☐
38		C	M-F	4.00	0.10	X		☐	☐	☐
39		C	M-B	1.20	0.20	X		☐	☐	☐
40		C	M-F	2.00	0.03	X	X	☑	☐	☐
41		C	B	1.50	0.30	X		☐	☐	☐
42		C	M-F	6.00	0.05	X		☐	☐	☐
43		C	F	10.00	0.05	X		☐	☐	☐
44		C	F	3.00	0.01	X		☐	☐	☐
45		C	C-F	9.00	0.05	X		☐	☐	☐
46		C	F	7.80	0.05	X		☐	☐	☐
47		C	F	3.60	0.03	X		☐	☐	☐
48		C	M-B	10.00	0.20	X		☐	☐	☐
49		C	M-B	10.50	0.30	X		☐	☐	☐
50		C	C-B	2.00	0.20	X	X	☑	☐	☐
51		C	B	1.80	0.10	X		☐	☐	☐
52		C	M-F	13.00	0.10	X		☐	☐	☐
53		C	C-B	21.00	0.20	X		☐	☐	☐
54	E9-D4	C	C-B	4.00	0.03	X		☐	☐	☐
55		C	C-F	2.40	0.03	X		☐	☐	☐
56		C	F	2.60	0.02	X		☐	☐	☐
57		C	F	1.70	0.03	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
58		C	C-F	1.40	0.02	X		☐	☐	☐
59		C	C-B	8.00	0.05	X		☐	☐	☐
60		C	C-B	30.00	0.05	X	X	☑	☐	☐
61		C	M-B	7.20	0.20	X		☐	☐	☐
62		C	M-B	10.00	0.10	X		☐	☐	☐
63		C	C-F	5.50	0.03	X		☐	☐	☐
64		C	F	0.80	0.03	X		☐	☐	☐
65	D7	C	F	10.00	0.05	X		☐	☐	☐
66		C	F	3.00	0.05	X		☐	☐	☐
67		C	F	1.00	0.05	X		☐	☐	☐
68		C	B	6.00	0.10	X		☐	☐	☐
69		C	C-B	3.20	0.05	X		☐	☐	☐
70		C	M-F	1.80	0.03	X	X	☑	☐	☐
71		C	C-B	14.00	0.20	X		☐	☐	☐
72		C	M-F	11.00	0.03	X		☐	☐	☐
73		C	M-F	30.00	0.05	X		☐	☐	☐
74		C	B	2.40	0.20	X		☐	☐	☐
75		C	M-F	1.60	0.10	X		☐	☐	☐
76	G7	C	B	18.00	0.20	X		☐	☐	☐
77		C	M-F	10.00	0.05	X		☐	☐	☐
78		C	F	1.20	0.05	X		☐	☐	☐
79		C	C-F	16.00	0.10	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
80		C	C-B	8.00	0.20	X	X	☑	☐	☐
81		C	F	5.60	0.10	X		☐	☐	☐
82		C	B	1.40	0.10	X		☐	☐	☐
83		C	C-F	16.00	0.03	X		☐	☐	☐
84		C	M-B	2.80	0.20	X		☐	☐	☐
85		C	M-F	2.20	0.03	X		☐	☐	☐
86		C	M-B	4.40	0.05	X		☐	☐	☐
87		C	C-F	12.00	0.05	X		☐	☐	☐
88		C	M-F	16.00	0.03	X		☐	☐	☐
89	G4	C	B	1.00	0.20	X		☐	☐	☐
90		C	M-F	8.00	0.03	X	X	☑	☐	☐
91		C	B	2.50	0.25	X		☐	☐	☐
92		C	B	32.00	0.10	X		☐	☐	☐
93		C	B	6.00	0.30	X		☐	☐	☐
94		C	F	1.40	0.03	X		☐	☐	☐
95		C	B	2.20	0.10	X		☐	☐	☐
96		C	C-F	4.50	0.05	X		☐	☐	☐
97		C	B	1.50	0.03	X		☐	☐	☐
98		C	C-B	40.00	0.10	X		☐	☐	☐
99		C	B	2.20	0.08	X		☐	☐	☐
100		C	B	13.00	0.20	X	X	☑	☐	☐
101		C	M-B	2.50	0.10	X		☐	☐	☐

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster

Str#:	SquareID:	Type:	Structure:	Length	Width	Morph:	SAED:	EDS:	Photo:	Sketch:
102		C	F	3.80	0.03	X		☐	☐	☐
103		C	B	2.20	0.10	X		☐	☐	☐
104		C	M-F	2.00	0.05	X		☐	☐	☐
105		C	F	1.20	0.05	X		☐	☐	☐
106		C	M-F	10.50	0.10	X		☐	☐	☐
107		C	F	1.00	0.03	X		☐	☐	☐
108		C	M-F	1.80	0.03	X		☐	☐	☐

M40633 002

C - Chrysotile
TR - Tremolite
CR - Crocidolite
AN - Anthophyllite
AC - Actinolite

NSD - No Structure Detected
F - Fiber
B - Bundle
M - Matrix
C - Cluster


Realtime: 36.0
Livetime: 34.3
M40633-002 Chrysotile Str # 1:
103
77
51
25
Counts
Cu
Cu
Mg
Si
Cu
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 31:4
Livetime: 27:2
M40633-002 Chrysotile Str = 2::
Counts
103
77
51
25
Si
Cu
Mg
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 25.2
M40633-002 Chrysotile Str # 3::
Counts
103
77
51
25
Cu
Si
Cu
Mg
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 30.3
Livetime: 27.2
M40633-00Z Chrysotile Str # 4::
Cu
103
77
Mg
Si
51
Counts
25
Cu
Cl
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 322.2
Livetime: 307.0
M40633-002 Chrysotile Str #5::
246
184
123
61
Counts
Cu
Mg
Si
Cu
Fe
Cu
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)


Realtime: 54.7
Livetime: 51.0
M4D633-002 Chrysotile Str # 6:1
246
184
123
61
Counts
Si
Mg
Cu
Fe
Cl
0.000
1.280
2.560
3.840
5.120
6.400
7.680
8.960
10.240
X-Ray Energy (KeV)